

# deKoll®

PREMIX PER L'EDILIZIA

SUPPORT TREATMENT

**PINTOCOLOR®**  
TUTTI I MIEI COLORI

**termax®**  
SALVA ENERGIA

<<  
2018 - 2022  
2119 - 2120

# RECOMMENDATIONS FOR THE TREATMENT OF SUPPORTS FOR THE INSTALLATION OF BASIC PRODUCTS (EXISTING REPAIRS/NEW APPLICATION)



**deKoll**<sup>®</sup>  
PREMIX PER L'EDILIZIA

## SUPPORT TREATMENT

### - FOR FILLING MORTAR (FOR PLASTERING)

#### SUPPORT

1. Concrete
2. Ceramic Brick( Red)
3. Silicate Brick(Lightweight)
4. Stone

#### Application

- Plastering mortar
- Plastering mortar
- Plastering mortar
- Plastering mortar

#### SURFACE TREATMENT

- Concrete Primer (Dilution 10%-20%)
- No need to treat the support
- Acrylic Primer (Dilution 1:2)
- Beton Primer (Dilution 10%-20%)

### -FOR TILE ADHESIVES

#### SUPORTI

1. Existing plate
2. Weak substate 3-6 months
3. Weak substate over 6 months
4. Concrete
5. Quartz concrete

#### APPLICATIONS

- Tile on tile
- Tile
- Tile
- Mosaic/ Swimming pool tile
- Tile

#### TRAJTIMI SIPËRFAQES

- Beton Primer (Dilution 10%-20%)
- Primer D (1:2) / Astar Akrilik (1:4)
- Primer D (1:2) / Astar Akrilik (1:4)
- Beton Primer (Dilution 10%-20%)
- Beton Primer (Dilution 10%-20%)

## ATTENTION!

**\*Based on the technical data sheets, for supports (new layers) that are clean, stable, only wetting the support with water and direct application of tile adhesives is recommended.**

## -PFOR SELF-LEVELING COMPOUND (DEKOFLOOR)

### - SUPPORT

- 1.Existing Tiles
- 2.Weak substate 3-6 months
- 3.Weak substate over 6 months
- 4.Quartz concrete

### APPLICATION

Dekofloor  
Dekofloor  
Dekofloor  
Dekofloor

### SURFACE TREATMENT

Beton Primer (Dilution 10%-20%)  
Primer D (Dilution 1:2)  
Primer D (Dilution 1:2)  
Beton Primer (Dilution 10%-20%)

## -FINISH APPLICATION (FINO / PUTTY) SUPPORT

1. Fino painted with hydro-matt paint
- 2.Fino painted with plastic paint
- 3.Plaster (base coat mortar)

### APPLICATION

Decorative putty  
Decorative putty  
Leveling + Fino

### SURFACE TREATMENT

Sanding + Acrylic Primer (1:3)  
Sanding + Acrylic Primer (1:3)  
Two coats of leveling compound  
with mesh (leveling compound  
with low mechanical strength)

## -PËR SISTEM TERMOIZOLIMI (KAPOT)

### SUPPORT

1. Fino painted with acrylic  
paint
- 2.Existing textured finish or  
damaged structure, cracks  
over ETICS system

### APPLICATION

EPS / Glass  
Fiber / Rock Wool  
  
Decorative Finish

### SURFACE TREATMENT

Surface tapping + Concrete Primer  
(Dilution 10%-20%) + Polystyrene  
adhesive  
  
Concrete Primer (Dilution 10%-20%)  
+ Leveling adhesive + mesh

## ATTENTION!

**For all the above-mentioned cases, during the application and curing phase of the product, temperatures must not be lower than +5°C or higher than +35°C. Both low and high temperatures may alter the product's working characteristics (slowing down or accelerating the drying process). The dilution ratio with water for different primers must also be respected.**





# OUR PROJECTS



ONE ORICUM BAY



GREEN COAST 2



ORIKUS CANYON



PODIUM OF ORIKUM



PAZARI I RI




LAGJA NDROQ

## Dekoll is everywhere!

- Kosovo
- Macedonia
- Swiss
- Serbia
- Italy
- Cyprus
- France
- Germany
- Lebanon
- Bahrain
- Oman
- UAE
- Qatar
- UAE
- Montenegro

### Na kontakti:

(+355) 69 808 0122/ [info@dekoll.al](mailto:info@dekoll.al)



DEKOLL\_EU

**dekoll**<sup>®</sup>  
PREMIX PER L'EDILIZIA